

## Stickler PP Clear TC AP901



### Quick Overview

Stickler PP Clear TC Clear Gloss is a clear polypropylene top coated film designed for ultimate label application conformation on many difficult and contoured surfaces. Supplied with good clarity for optimum print results, and label performance gives the stock a cloud free/high resolution finish.

### Details

Stickler PP Clear TC Clear Gloss is a clear polypropylene top coated film designed for ultimate label application conformation on many difficult and contoured surfaces. Supplied with good clarity for optimum print results, and label performance gives the stock a cloud free/high resolution finish.

### Applications

Recommended for labels where a durable face-stock is required, eg. Prime labels for body care

### Technical Data

#### Face Material:

Properties	Test Method	Result
Grammage	ISO 536	45 g/m <sup>2</sup>
Caliper	ISO 534	50 microns
UV exposure	Depending on ink coverage:	6 month

#### Adhesive: AP901 General Purpose Permanent

Permanent pure acrylic adhesive designed for films. Featuring high cohesion, good clarity and very good performance on apolar substrates (PE,PP), approved for direct contact on the skin (plasters)

Properties	Test Method
Composition	Water based acrylic
Direct sunlight resistance	Excellent
Cohesion	High
Application temperature (min)	-5°C
Service Temperature	-40°C + 120°C
Tack FTM9	8N/Inch
Ultimate adhesion FTM2	7N/Inch

#### Laminate:

Laminate shelf life	24 months stored at 20°C/50%RH
Typical laminate	124±6ums
Total weight	130±6

---

## Backing

### WG White Glassine

1 side siliconised supercalendered white glassine

<b>Properties</b>	<b>Result</b>
Grammage	65 gsm
Caliper	56 microns
Transparency	>40%

---

## Important Note

All statements, technical information and recommendation are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed, and the following is made in lieu of all warranties of merchantability and fitness for the purpose: Sellers and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Before using, user shall determine the suitability of the product for its intended use, and user assumes all risk and liability whatsoever in connection therewith.